


AGILENT INTERNATIONAL CO., LIMITED

MSH 2896 RM 1007, 10/F HO KING CTR 2-16 FA YUEN ST. MONG KOK KL. HK

The following sample(s) was/were submitted and identified by the client as:

Sample Description : LAMINATE FLOORING
Style No. : FORTHFLOOR MASTER
P.O. No. : LOTE 42
Country of Origin : CHINA
Sample Receiving Date : MAY, 23, 2011
Testing Period : MAY, 23, 2011 TO JUN. 07, 2011
Test Performed : SELECTED TEST(S) AS REQUESTED BY APPLICANT
Test Requested : ABRASION RESISTANCE
(EN 13329:2006 + A1:2008, ANNEX E)
Test Result(s) : FOR FURTHER DETAILS, PLEASE REFER TO THE
FOLLOWING PAGE(S)
Conclusion : THE SUBMITTED SAMPLE MET THE TEST
REQUIREMENT.

Signed for and on behalf of
SGS-CSTC Ltd.Rainbow Wang
Section Head

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, jurisdiction and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its inspection only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SHHG 798151



Test Report

No.: SHHG1105011823BM

Date: JUN. 16,2011

Page: 2 of 3

Test Conducted :

Abrasion Resistance (EN 13329:2006 + A1:2008, Annex E)

Test Result:

Test Property	Test Requirements						Test Result
Abrasion resistance	Prepare two wheels with preconditioned unused abrasive paper from the same batch previously approved by calibration. Lower the wheels. start the suction device and abrade the test specimen. Examine the test specimen for abrasion after each 100 revolutions and renew the abrasive papers after every 200 revolutions. Continue the test in this way until the initial wear point (IP) is reached. The initial wear point is reached when there are areas of at least 0.60 mm ² wear-through in two quadrants and an area of 0.60 mm ² wear-through becomes visible in a third quadrant. Record the number of revolutions as the IP-value. Repeat the test immediately using the two remaining tests immediately using the two remaining test specimens.						Pass Claim:AC3 Average IP value: 3200 cycle Abrasion class: AC3
	Abrasion class	AC1	AC2	AC3	AC4	AC5	
	Average IP-value	≥900	≥1500	≥2000	≥4000	≥6000	

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755)83911443, or email: CN.Docscheck@sgs.com

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its inspection only and, within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



SHHG 798152


Sample Photo:

Test Sample(front view)



Test sample(back view)

(FORTHFLOOR MASTER AC3 2011/05/10
14:50:39 42)



End of Report

Attention: To check the authenticity of testing / inspection report & certificates, please contact us at telephones: (86-750)83371441, or email: CN_Docs@sgs.com

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, independence and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



SHHG 798153